

POWERSIL[®] 466 A/B

Liquid Silicone Rubber (LSR)

POWERSIL[®] 466 A/B is a liquid silicone rubber with medium conductivity, stable electrical properties and good mechanical properties.

Properties

- high elongation at break, low tension set
- stable electrical properties
- good mechanical properties
- ready-to-use, two-component system

Specific features

- Cold-shrinkable
- Electrically conductive

Technical data

Properties Uncured

Property	Condition	Value	Method
Viscosity, dynamic of Component A (10 s ⁻¹)	-	600000 mPa·s	DIN EN ISO 3219
Viscosity, dynamic of Component B (10 s ⁻¹)	-	500000 mPa·s	DIN EN ISO 3219
Mix ratio	-	1 : 1	A : B

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Catalyzed A+B

Property	Condition	Value	Method
Viscosity, dynamic (10 s ⁻¹)	-	550000 mPa·s	DIN EN ISO 3219
Kick-off temperature	-	125 °C	-
Pot Life	23 °C	3 d	-

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

Cure conditions: 5 min / 165 °C in press; Postcuring 4 h / 200 °C

Property	Condition	Value	Method
Appearance	-	black	-
Hardness Shore A	-	38	DIN ISO 48-4
Density	-	1.08 g/cm ³	DIN EN ISO 1183-1 A
Tensile strength	-	7.0 N/mm ²	ISO 37 type 1
Elongation at break	-	650 %	ISO 37 type 1
Tear strength	-	28 N/mm	ASTM D 624 B
Compression Set ⁽¹⁾	22 h 175 °C	11 %	DIN ISO 815-1 type B method A
Volume resistivity	-	30 Ohmcm	IEC 62631-3-1
Modulus at 100 % elongation	-	0.75 N/mm ²	ISO 37 type 1
Modulus at 300 % elongation	-	2.6 N/mm ²	ISO 37 type 1
Tension set	-	2.6 %	ISO 2285

¹post-cured 6 h / 200 °C

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Cable Accessories

Application details

POWERSIL® 466 A/B is suitable for production of electrically conductive injection moulded articles, especially cable accessories in the medium and high voltage range. The range of use spreads from push-on accessories to cold shrink applications. POWERSIL® 466 A/B combines a low Shore A durometer with high elongation, good setting properties (low tension set) and good mechanical properties which are a must for cold shrink applications.

Processing

Components A and B are delivered ready to use in drums of 20 and 200 litres capacity. They can be pumped by means of standard metering equipment from these drums and mixing in a static mixer straight into the heated mold.

The mixing ratio is 1 : 1. At room temperature, mixtures of A and B components have a pot life of at least three days.

For detailed information, refer to brochures on www.wacker.com.

Packaging and storage

Packaging

This product is available in 20 kg pail and 200 kg drum kits.

Storage

The 'Best use before end' date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code POWERSIL® 466 A/B



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Gisela-Stein-Strasse 1, 81671 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.