

SILRES® BS 34 US



Silicone Fluid Emulsions, functional

SILRES® BS 34 US is a stable, low VOC silicone and organic polymer containing water-based emulsion. When applied to a substrate it forms a stable, penetrating water repellent for enhancing a wide variety of porous mineral surface including concrete, natural and artificial stone and unglazed ceramic tile.

SILRES® BS 34 US is not recommended for below grade applications where hydrostatic pressure can be significant.



Properties

- Beads liquids
- Very Low VOC
- Improved UV Stability
- Provides excellent water repellency to reduce cracking, spalling, freeze/thaw damage, chemical degradation, efflorescence, and dirt pickup, thereby lengthening substrate life and reducing maintenance costs.
- Enhances the features of the substrate providing a vibrant appearance
- Repels water, hindering penetration, maintaining a consistent appearance
- Physically and chemically bonds to substrates increasing the service life, making cleaning easier, thereby reducing maintenance and replacement costs
- Suitable for interior or exterior decorative stone and concrete projects

Technical data

General Characteristics

| Property | Condition | Value | Method |
|-----------------|-----------|---------------------------------|--------|
| pH | - | 8 - 10 | - |
| Actives Content | - | 26 - 30 % | - |
| Density | 22 °C | 0.995 - 1.125 g/cm ³ | - |

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Concrete Protection
- Hydrophobic Impregnation
- Stone Color Enhancement

Application details

Surface Preparation

Surface preparation depends on substrate placement, type and strength, curing and finishing processes, age, condition, previous contamination, and the presence of previous coatings. Surfaces should be clean from dust, dirt, oils, grease, curing compounds, other coatings, efflorescence, and laitance before applying SILRES® BS 34 US.

Cleaning methods which are compatible with the application of SILRES® BS 34 US include:

- Mechanical: abrasive blasting (sand, baking soda, vacuum).
- Chemical: acid etching, stripping, solvent de-greasing, caustic soda scrubbing, alkaline soap scrubbing, high pressure washing, high pressure washing with sand.
- Heat: propane and acetylene torching.

If strongly acidic or caustic cleaning agents are used, neutralize the surface and completely wash to remove any residues. Before using any surface preparation method, a test patch should be performed with the customer's approval to ensure desired results are achieved.

New concrete should be allowed to cure for at least 28 days before applying SILRES® BS 34 US. Substrate moisture level below 4% promotes penetration of product.

SILRES® BS 34 US is intended to be used at full strength or may be blended with water to desired ratio.

Mix before each use.

SILRES® BS 34 US emulsions can be applied by brush, sponge, roller or pump-up garden sprayer. Multiple coats may be applied wet-on-wet.

Do not allow product to pool. Remove excess material before it cures.

Water repellency starts to develop within 24 hours.

A test patch should be performed prior to general application with the customer's approval to ensure that desired appearance and water repellency are achieved. It is advisable to test the product in an inconspicuous area.

Surfaces treated with SILRES® BS 34 US should be cleaned as soon as they have been exposed to contaminant. Paint is very difficult to remove once it has completely cured.

Treated surfaces should be dry and protected within 24 hours.

Packaging and storage

Storage

Storage

The "Best use before end date" of each batch is shown on the Certificate of Analysis. Storage beyond the date specified on the Certificate of Analysis does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

For specific information regarding safe handling of this material, please refer to the Safety Data Sheet.

QR Code SILRES® BS 34 US



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Gisela-Stein-Strasse 1, 81671 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.