

GENIOSIL[®] APTE




Organofunctional Silanes

3-Aminopropyltriethoxysilane

GENIOSIL[®] APTE is a clear, colorless liquid with a characteristic amine odor.

CAS No. 919-30-2 | Empirical formula $C_9H_{23}NO_3Si$ | Molecular weight 221,37 g/mol



Properties

GENIOSIL[®] APTE is an alkoxy silane with an amino-functional group. It's a clear, colorless liquid with a characteristic amine odor. Due to the nature of the amino group, this substance reacts as a strong base. The silane hydrolyzes autocatalytically in the presence of moisture (ethanol is released) to form silanols, which can subsequently react with themselves to produce siloxanes or can bind to inorganic substrates. As a typical amine, GENIOSIL[®] APTE can also interact with numerous organic polymers and thus function as a molecular bridge between organic and inorganic substrates.

In addition to its application as an adhesion promoter in formulations and primers, GENIOSIL[®] APTE functions as a surface modifier for fillers and pigments, where it improves the dispersibility of the filler and the mechanical properties - such as flexural strength, tensile strength and modulus - of the composites. The silane also reduces the filler's sedimentation tendency in the uncured polymer. GENIOSIL[®] APTE also greatly increases water (vapor) and corrosion resistance.

Technical data

General Characteristics

Property	Condition	Value	Method
Amine equivalent number	-	4.5 mmol/g	WSTM 1297A
Appearance	-	clear liquid	-
Boiling point	1013 hPa	217 °C	Lit.
Density	25 °C	0.94 g/cm ³	DIN 51757
Purity	-	> 97.0 %	-
Refractive index	25 °C	1.42	-
Viscosity, dynamic	25 °C	approx. 1.6 mPa·s	DIN 51562

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Adhesives
- Building & Construction Adhesives
- Chemical Industry
- Composites
- Industrial Adhesives
- Industrial Coatings
- Insulation Materials
- Primers for Paints & Coatings
- Sealants
- Thermoplastics & Elastomers

Application details

1. General processing information:

GENIOSIL® APTE is highly miscible with standard organic solvents such as ethers and hydrocarbons.

Mixing with ketones results in imine formation, while mixing with alcohols other than ethanol leads to an autocatalytic exchange of alkoxy groups until the system reaches thermodynamic equilibrium.

GENIOSIL® APTE shows typical amine behavior when exposed to acids, epoxides or isocyanates.

GENIOSIL® APTE is highly soluble in neutral water and undergoes hydrolysis.

Caution: due to the enthalpy of solution, mixing GENIOSIL® APTE with water is exothermic. A solution of GENIOSIL® APTE in water has a pH of 10 - 11 and remains stable for several weeks. Due to the highly reactive nature of GENIOSIL® APTE, contact with moisture must be avoided during processing to prevent undesired hydrolysis.

2. GENIOSIL® APTE as a surface modifier:

Fillers are treated either with pure GENIOSIL® APTE or a solution thereof. It may be necessary to pretreat the substrate with water. The modified filler is preferably bonded to the organic material, e.g. an epoxy resin, by mixing it with a standard curing agent.

In an alternative procedure referred to as "blending", GENIOSIL® APTE is added directly to the polymer - either before the organic materials is compounded with the filler or at the same time.

A prerequisite for the blending process is that GENIOSIL® APTE and the polymer are compatible and that the resin and GENIOSIL® APTE do not react prematurely.

3. GENIOSIL® APTE as an adhesion promoter in formulations:

In silane crosslinking formulations (e.g. silane-terminated polyethers or polyurethanes and polysiloxanes), GENIOSIL® APTE may be added to the formulation as an adhesion promoter. Processing is effected by means of standard mixing methods.

Usually, about 1 - 2 wt % silane is added to the formulation.

Packaging and storage

Packaging

GENIOSIL® APTE is available in different packaging units:

- Tankcontainer
- 950 KG IBC
- 180 KG Drum
- 25 KG Can

Storage

The 'Best use before end' date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code GENIOSIL® APTE



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Gisela-Stein-Strasse 1, 81671 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.