WACKER

CENUSIL® M 830 A/B

Room Temperature Curing Silicone Rubber (RTV-2)

is a pourable, addition-curing RTV-2 silicone rubber that cures at room temperature.

Main application: Making molds for concrete casting. Food contact (FDA/ BfR compliant).



Properties

- good flow ability and self-deaeration
- proper tear strength
- universal hardness (26 Shore A)
- easy to meter and mix due to 1 : 1 ratio
- perfect and non-shrink cure at room temperature which can be accelerated considerably by the application of heat
- excellent long- term stability of the mechanical properties of the vulcanizate
- good resistance to common reproduction materials

Specific features

- Addition Curing
- BfR compliant
- FDA compliant
- Flowable
- Food-contact
- No chemical shrinkage
- Resistance against concrete
- Two-component

Technical data

Properties Uncured

Property	Condition	A	В	Method
Color	-	translucent	translucent	-
Density	23 °C	1.05 g/cm ³	1.05 g/cm ³	DIN EN ISO 2811-1
Viscosity, dynamic	23 °C	8000 mPa·s	8000 mPa·s	ISO 3219

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Catalyzed A+B

Property	Condition	Value	Method
Mix ratio	-	1:1	-
Pot Life ⁽¹⁾	23 °C	60 min	DIN EN ISO 2555
Demoldable at 23°C after	-	14 - 16 h	-

¹up to 100000 mPas

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

After 24 hours at 23 °C

Property	Condition	Value	Method
Color	-	translucent	-
Tear strength	-	> 20 N/mm	ASTM D 624 B
Hardness Shore A	-	26	DIN ISO 48-4
Tensile strength	-	5 N/mm ²	ISO 37 type 1
Elongation at break	-	500 %	ISO 37 type 1

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Composite molding
- Construction Molding

CENUSIL® M 830 A/B | Most recent change: 16.06.2024

- Mold Making of Vacuum Bags
- Reproduction Molding

Application details

As a medium-Shore A addition RTV-2 silicone rubber that cures without undergoing dimensional shrinkage, CENUSIL® M 830 A/B is extremely suitable for casting all common reproduction materials.

Processing

Important note:

The platinum catalyst is contained in Component A

Caution

A and B components may only be used together if they have the same batch number.

To ensure optimum flow of the material, the components must be stirred thoroughly before they are removed, or processed in their containers.

Please check also our brochures and info sheets.

Packaging and storage

Packaging

- CENUSIL® M 830 A 20 KG HOBBOCK PE
- CENUSIL® M 830 A 200 KG DRUM SB
- CENUSIL® M 830 B 20 KG HOBBOCK PE
- CENUSIL® M 830 B 200 KG DRUM SB

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Components A and B of the addition-curing grade CENUSIL® M 830 A/B contain only constituents that over many years have proved to be neither toxic nor aggressive. Special handling precautions are therefore not required, i.e., only the general industrial hygiene regulations apply.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site http://www.wacker.com.

QR Code CENUSIL® M 830 A/B



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Gisela-Stein-Strasse 1, 81671 Munich, Germany productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.