

# VINNEX<sup>®</sup> 8803

## Polyvinyl Acetate & Copolymers

VINNEX<sup>®</sup> 8803 is an innovative compound based on vinyl acetate/vinyl laurate copolymer and polyvinyl acetate.

### Properties

- VINNEX<sup>®</sup> 8803 is a colorless, tasteless and odorless thermoplastic resin in dosable form and can be melted easily.

### Technical data

#### Specification

Property	Condition	Value	Method
Free acetic acid	-	max. 0.05 %	specific method
Residual monomer (vinyl acetate)	-	max. 5 ppm	specific method
Residual monomer (vinyl laurate)	-	max. 100 ppm	specific method
Viscosity, 10 % in ethyl acetate	20 °C	5.0 - 7.0 mPa·s	ASTM D 445 - 06

## General Characteristics

Property	Condition	Value	Method
Mettler Softening Point	-	approx. 118 °C	ASTM D 3104
Glass transition temperature	-	approx. 25 °C	DSC (DIN 53765 / ISO 11357-5)
Appearance	-	solid, colorless beads	Visual
Volatiles	-	max. 1 %	specific method

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

## Applications

- Additives for Biopolymers
- PBS Applications
- PHA/PHB Applications
- PLA Applications
- Resin Modification for Composites

## Application details

VINNEX® 8803 is recommended as highly efficient Low Profile Additive for fiber-reinforced composites and polymer concrete type applications. Guide formulations are available upon request. It also shows excellent compatibility with Biopolyesters like PLA.

### Processing

Solid content Viscosity Brookfield RVT  
in styrene 20 RPM, 23 ° C (P ML 002)

40 % 1100 mPas

Solid content Viscosity Brookfield RVT  
in 1,4-BDDMA 20 RPM, 23 ° C (P ML 002)

33 % 3100 mPas

### Additional information

If the product is used in applications other than those mentioned, the choice, processing and use of the product is the sole responsibility of the purchaser. All legal and other regulations must be complied with.

For questions concerning food contact status according the chapter 21 CFR (US FDA) and German BfR, please feel free to contact us.

Wacker Chemie AG  
Gisela-Stein-Strasse 1  
81671 Munich  
Germany

## Packaging and storage

### Packaging

VINNEX® 8803 is delivered in 25 kg bags.

### Storage

To prevent caking VINNEX® 8803 should not be stored at temperatures above 10°C. Storage conditions must be dry; material must be protected from direct sun exposure.

Under these conditions the product has a shelf life of at least 36 months starting from the date of receipt.

## Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

## QR Code VINNEX® 8803



### For technical, quality or product safety questions, please contact:

**Wacker Chemie AG**, Gisela-Stein-Strasse 1, 81671 Munich, Germany  
[productinformation@wacker.com](mailto:productinformation@wacker.com), [www.wacker.com](http://www.wacker.com)

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.