

# VINNOL® E 22/48 A



## Vinyl chloride Co- and Terpolymers

VINNOL® E 22/48 A is a hydroxyl-containing copolymer of approx. 75 wt.% vinyl chloride (VC) and approx. 25 wt.% carbon acid esters.

Its main use is as a binder for surface coating compounds and printing inks.

## Properties

VINNOL® E 22/48 A is a thermoplastic, physically drying binder that forms a film when the solvent contained in the formulation has evaporated.

Like all VC copolymers, VINNOL® E 22/48 A is extremely tough, showing permanent flexibility, abrasion resistance, little tendency to swell in the presence of water and low gas permeability. It is also highly resistant to oil, grease, dilute aqueous acids, alkalis and saline solutions, as well as to aliphatic hydrocarbons, such as white spirit, and alcohols.

## Special Features

VINNOL® E 22/48 A contains approx. 1.8 wt. % free hydroxyl groups and can therefore also be used as a reactant or co-binder in two-pack systems. For example, it may be crosslinked with isocyanates, epoxy or melamine resins.

## Technical data

### Specification

Property	Condition	Value	Method
K-value	-	47 - 49	DIN EN ISO 1628-2
Viscosity, dynamic (20% in MEK) <sup>(1)</sup>	20 °C	38 - 52 mPa·s	DIN 53015 (20°C)
Chlorine content	-	42.0 - 43.2 wt. %	specific method
Volatiles	-	< 0.7 wt. %	specific method

<sup>1</sup>after dissolving at 50 °C

### General Characteristics

Property	Condition	Value	Method
Efflux time (20% in MEK)	-	approx. 46 s	DIN EN ISO 2431 (4 mm)
Supply form	-	white granulate with some powder	Visual
Glass transition temperature	-	approx. 61 °C	DSC (DIN 53765 / ISO 11357-5)
Molecular weight (Mw)	-	60000 - 80000 g/mol	SEC, PS-Standard
Particle size	-	< 2.5 mm	specific method

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

## Applications

- Anti-Corrosive Coatings
- Coil Coatings
- Gravure Printing
- Industrial Wood Coatings
- Inkjet
- Marine & Protective Coatings
- Pad Printing
- Plastic Coatings
- Screen Printing
- Transfer Printing

## Application details

Typical applications for VINNOL® E 22/48 A:

- Primers
- Intermediate coatings
- Two-pack coating systems
- Baking finishes
- Adhesives
- Printing inks
- Magnetic tape coatings

## Processing

VINNOL® E 22/48 A is generally used in dissolved form.

Ketones and esters are the solvents most commonly used for VINNOL® E 22/48 A. Ketones, in particular, are excellent solvents for VINNOL® surface coating resins. In the case of VINNOL® E 22/48 A, esters, too, may be used as single solvents. Of the chlorinated hydrocarbons, methylene chloride and 1,2-dichloroethane are true solvents, while tri- and tetrachloroethene have only a swelling effect. Alcohols and aliphatic hydrocarbons do not dissolve VINNOL® E 22/48 A. Aromatic hydrocarbons may be combined to a limited extent with true solvents.

VINNOL® E 22/48 A can be plasticized with monomeric and polymeric plasticizers such as phthalates, adipates, sebacates, citrates, phosphates, epoxides and chlorinated paraffins.

VINNOL® E 22/48 A is fully compatible with all other VINNOL® surface coating resins. It also combines well with a large number of acrylic polymers and ketone resins, plus epoxides, polyurethane and alkyd resins. Polyvinyl acetates and polyvinyl butyrals are in general incompatible with VINNOL® E 22/48 A, while ester-soluble nitrocellulose is compatible to a certain degree. We recommend always checking the compatibility of VINNOL® E 22/48 A with the polymer in question.

VINNOL® E 22/48 A shows good compatibility with the pigments and fillers routinely used in the coatings industry. Care must be taken when using pigments containing zinc or cadmium because these catalyze the decomposition of VC copolymers at elevated temperatures. The same applies to iron-oxide pigments.

Despite good inherent stability, it is necessary for some applications to stabilize coatings based on VINNOL® E 22/48 A against heat and/or UV light. Epoxy compounds often suffice to stabilize these coatings against low thermal impact. Where higher temperatures are involved, it is advisable to use calcium/zinc or organotin stabilizers. Outdoor applications require the additional use of UV stabilizers along with thermal stabilizers optimized for these conditions.

To avoid risk of discoloration, contact with iron should be avoided both during preparation of the solution and during subsequent storage of the product. VINNOL® -based surface coating compounds should be stored in coated containers.

## Additional information

If the product is used in applications other than those mentioned, the choice, processing and use of the product is the sole responsibility of the purchaser. All legal and other regulations must be complied with.

For questions concerning food contact status according the chapter 21 CFR (US FDA) and German BfR, please feel free to contact us.

Wacker Chemie AG  
Gisela-Stein-Strasse 1  
81671 Munich  
Germany

## Packaging and storage

### Packaging

VINNOL® E 22/48 A is packed in 25-kg, coated three-ply paper bags containing a polyethylene liner.

### Storage

Store VINNOL® E 22/48 A under dry conditions and at room temperature (below 25 °C). If proper conditions are maintained, the product has a shelf life of at least 12 months from the delivery date if stored in the original, unopened containers. Beyond its recommended shelf life, the product is not necessarily unusable, but the user should perform quality control regarding the properties relevant to the application.

## Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. These are available on request from WACKER sales offices or may be downloaded from the WACKER Web site [www.wacker.com/vinnol](http://www.wacker.com/vinnol).

## QR Code VINNOL® E 22/48 A



### For technical, quality or product safety questions, please contact:

**Wacker Chemie AG**, Gisela-Stein-Strasse 1, 81671 Munich, Germany  
[productinformation@wacker.com](mailto:productinformation@wacker.com), [www.wacker.com](http://www.wacker.com)

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.