

# ELASTOSIL® RT 771



## Room Temperature Curing Silicone Rubber (RTV-2)

ELASTOSIL® RT 771 is a self-levelling, condensation curing RTV-2 silicone adhesive. When processed with a curing agent of the WACKER® Catalyst T 77 series, a self-bonding and durable silicone rubber is formed.

Cured ELASTOSIL® RT 771 shows long-term stability against weathering, moisture and UV light. The silicone elastomer may continuously be exposed to constantly changing climatic conditions, UV radiation and temperatures as high as 180 °C (356 °F) without damage.

## Properties

Uncured:

- High extrusion rate
- Self-levelling
- Fast curing at room temperature
- To be cured with WACKER® Catalyst T 77 or WACKER® Catalyst T 77 PLUS (recommended mixing ratio: 10:1)

Cured:

- Medium hardness
- Primerless adhesion to many substrates (glass, ceramics, metals, plastics and powder coatings)
- recommended service temperature range:

-50 °C to +180 °C

- Suitable for FIPG and, to a certain degree, for CIPG applications

## Specific features

- Condensation-curing
- Electrically insulating
- Media resistant
- Self-adhesive
- Shear thinning
- Thixotropic
- Two-component
- UV & weathering-resistant

## Technical data

### Properties Uncured

Property	Condition	Value	Method
Colour	-	creamy	-
Density	23 °C	approx. 1.53 g/cm <sup>3</sup>	DIN EN ISO 2811-2
Viscosity, dynamic	25 °C	150000 mPa·s	DIN EN ISO 3219

These figures are only intended as a guide and should not be used in preparing specifications.

### Catalyzed

Mixed with WACKER Catalyst T 77 (mixing ratio given in parts by weight)

Property	Condition	Value	Method
Viscosity of the mixture (10:1)	25 °C   0.5 1/s	approx. 250000 mPa·s	DIN EN ISO 3219
Viscosity of the mixture (10:1)	25 °C   25 1/s	approx. 45000 mPa·s	DIN EN ISO 3219
Pot Life (10:1)	23 °C	10 - 15 min	DIN EN ISO 3219
Pot Life (12:1)	23 °C	20 - 25 min	DIN EN ISO 3219
Pot Life (8:1)	23 °C	5 - 10 min	DIN EN ISO 3219
Tack-free time (10:1)	23 °C	approx. 60 min	-
Tack-free time (12:1)	23 °C	approx. 90 min	-
Tack-free time (8:1)	23 °C	approx. 45 min	-

These figures are only intended as a guide and should not be used in preparing specifications.

## Catalyzed

Mixed with WACKER Catalyst T 77 PLUS (mixing ratio given in parts by weight)

Property	Condition	Value	Method
Viscosity of the mixture (10:1)	25 °C   0.5 1/s	approx. 250000 mPa-s	DIN EN ISO 3219
Viscosity of the mixture (10:1)	25 °C   25 1/s	approx. 45000 mPa-s	DIN EN ISO 3219
Pot Life (10:1)	23 °C	5 - 8 min	DIN EN ISO 3219
Pot Life (12:1)	23 °C	8 - 12 min	DIN EN ISO 3219
Pot Life (8:1)	23 °C	4 - 6 min	DIN EN ISO 3219
Tack-free time (10:1)	23 °C	approx. 30 min	-
Tack-free time (12:1)	23 °C	approx. 45 min	-
Tack-free time (8:1)	23 °C	approx. 25 min	-

These figures are only intended as a guide and should not be used in preparing specifications.

## Properties Cured

Cured with WACKER Catalyst T 77 or WACKER Catalyst T 77 PLUS, mixing ratio 10:1 by weight. Curing Conditions: 14 days at 23 °C and 50 % rel. humidity, 2 mm sheet, no post-curing.

Property	Condition	Value	Method
Color	-	black	-
Density	23 °C	1.54 g/cm <sup>3</sup>	DIN EN ISO 1183-1 A
Hardness Shore A	-	45	DIN ISO 48-4
Tensile strength	-	1 N/mm <sup>2</sup>	ISO 37 type 1
Elongation at break	-	180 %	ISO 37 type 1

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

## Applications

- Machine Building
- Small Appliances
- White Goods

## Application details

- General purpose adhesive
- Typical fields of application: household appliances, automotive, mechanical engineering, electrical industry.

## Processing

Mixing and curing:

ELASTOSIL® RT 771 is processed in combination with a curing agent, such as WACKER® Catalyst T 77 or WACKER® Catalyst T 77 PLUS. Prior to application the two compounds should be thoroughly mixed, either manually or by automatic metering lines equipped with static or dynamic mixing devices. The recommended mixing ratio is 10:1 by weight.

Potlife and curing speed can be modified within limits by adjusting the ratio of base compound (ELASTOSIL® RT 771) to curing agent (WACKER® Catalyst T 77 or WACKER® Catalyst T 77 PLUS). Varying the mixing ratio between 8:1 and 12:1 usually has a small effect on the properties of the cured rubber. However, if the mixing ratio differs substantially from the recommended scope, preliminary tests should be carried out to check the cured material's suitability. General information about pot life and resulting curing times are given in the respective tables "Catalyzed".

Moreover curing speed can be slightly accelerated by raising the temperature. Heating, however, must not exceed 60 °C before curing is completed.

After completion of the vulcanization process the product may continuously be exposed to constantly changing climatic conditions, UV radiation and high temperature without damage. Cured ELASTOSIL® RT 771 usually shows good primerless adhesion to many substrates, e.g. glass, ceramics, metals, plastics and powder coatings.

Detailed information about processing and modifying curing speed is given in our brochure "ROOM TEMPERATURE VULCANIZING (RTV) SILICONES - MATERIAL AND PROCESSING GUIDELINES". We recommend running preliminary tests to optimize conditions for the particular application.

Removal:

If removal of the silicone from machines or dispensing equipment is necessary, white spirit or similar nonpolar solvents are recommended. However, cleaning ideally should take place before the silicone is fully vulcanized. Cured silicone needs to be removed mechanically, if necessary in combination with a swelling agent (solvent).

## Packaging and storage

### Storage

Store in a dry and cool place.

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

## Safety notes

While curing ELASTOSIL® RT 771 releases a total of approx. 1.5 - 2 wt.% alcohol. These vapors should not be inhaled for long periods or in high concentrations. Hence ventilation of the work place is recommended.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

## QR Code ELASTOSIL® RT 771



**For technical, quality or product safety questions, please contact:**

**Wacker Chemie AG**, Gisela-Stein-Strasse 1, 81671 Munich, Germany  
productinformation@wacker.com, [www.wacker.com](http://www.wacker.com)

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.