

# ELASTOSIL® VARIO 15

ELASTOSIL®

## Room Temperature Curing Silicone Rubber (RTV-2)

Pourable, addition-curing two-component silicone rubber that vulcanizes at room temperature.

Can be blended with ELASTOSIL® VARIO 40 to achieve any target hardness between 15 and 40 Shore A.

See our flyer:

"ELASTOSIL® VARIO MODULAR ADDITION CURING SYSTEM"



## Properties

- Two base components, two catalysts
- Easy to process because of low viscosity
- Fast and non-shrink cure at room temperature, adjustable over a wide range
- Low hardness 15 Shore A
- High elongation, outstanding tensile strength
- Excellent tear strength
- Cured rubber is translucent and colorless
- Can be pigmented with 1 - 4 % ELASTOSIL® Pigment Pastes FL

## Specific features

- Addition Curing
- BfR compliant
- FDA compliant
- Flowable
- Food-contact
- Low viscosity
- No chemical shrinkage
- Two-component

## Technical data

### Properties Uncured

Property	Condition	Value	Method
Color	-	Translucent	-
Density 23°C	-	1.06 g/cm <sup>3</sup>	DIN EN ISO 2811-1
Viscosity, dynamic 23°C, stirred	-	5.000 mPa·s	ISO 3219

These figures are only intended as a guide and should not be used in preparing specifications.

### Catalyzed

Property	Condition	Value	Method
Viscosity, dynamic 23°C	-	3.000 mPa·s	ISO 3219
Mix ratio with ELASTOSIL® Catalyst Vario or Catalyst Vario F	-	10 : 1 pbw	-
Pot Life 23°C, Catalyst Vario F, up to 100000 mPas	-	2 min	DIN EN ISO 2555
Pot Life 23°C, Catalyst Vario up to 100000 mPas	-	150 min	DIN EN ISO 2555
Demoldable 23° C with ELASTOSIL® Catalyst VARIO F	-	15 min	-
Demoldable 23°C with ELASTOSIL® Catalyst VARIO	-	6 h	-

These figures are only intended as a guide and should not be used in preparing specifications.

## Properties Cured

Curing conditions: 24 h / 23 °C

Property	Condition	Value	Method
Density 23°C in water	-	1.06 g/cm <sup>3</sup>	DIN EN ISO 1183-1 A
Tear strength	-	15	ASTM D 624 B
Hardness Shore A	-	15	DIN ISO 48-4
Tensile strength	-	6.5 N/mm <sup>2</sup>	ISO 37 type 1
Elongation at break	-	900 %	ISO 37 type 1

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

## Applications

- Prototype Molding
- Reproduction Molding

## Application details

Due to its resistance to all common reproduction materials. e.g. casting resins, concrete, plaster, as well as the mechanical properties, ELASTOSIL® VARIO 15 is especially suitable for all molds.

As a low Shore A addition silicone rubber that cures without undergoing dimensional shrinkage, ELASTOSIL® VARIO 15 is also suitable if absolutely accurate copies of models are required.

## Packaging and storage

### Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

## Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

## QR Code ELASTOSIL® VARIO 15



**For technical, quality or product safety questions, please contact:**

**Wacker Chemie AG**, Gisela-Stein-Strasse 1, 81671 Munich, Germany  
productinformation@wacker.com, [www.wacker.com](http://www.wacker.com)

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.