

# SILRES<sup>®</sup> IC 232



## Silicone Resins

SILRES<sup>®</sup> IC 232 is a solventless, reactive, methoxyfunctional methyl-phenyl polysiloxane with a narrow molecular weight distribution.

## Properties

Used to improve the weather and heat resistance of organic resins.

Is a solvent-free liquid resin.

Is FDA 21 CFR 175.300 and BfR XV compliant.

Can be used as a cold blend as well as chemically bound intermediates on organic polymers.

## Technical data

### General Characteristics

Property	Condition	Value	Method
Refractive index	25.0 °C	1.5 - 1.505	-
Appearance	-	clear, light straw-colored liquid	-
Alkoxy content	-	approx. 15 wt. %	-
Density	20 °C	1.14 g/cm <sup>3</sup>	DIN 51757
Total silicone content (all methoxy groups replaced by Si-O-Si bonds)	-	84 wt. %	-
Viscosity, dynamic	25 °C	approx. 120 mPa·s	DIN 51562
Volatiles	150 °C   1 h   5 g	< 2 wt. %	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

## Applications

- Coil Coatings
- Industrial Coatings
- Marine & Protective Coatings
- Resin Modification for Coatings

## Application details

SILRES® IC 232 is highly suitable for introducing a compatible silicone component into other binder systems to increase the weathering or heat resistance.

Guide formulations are available on request.

## Packaging and storage

### Packaging

1000 kg IBC  
220 kg drum  
30 kg can

### Storage

The "Best use before end" date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

## Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

## QR Code SILRES® IC 232



### For technical, quality or product safety questions, please contact:

**Wacker Chemie AG**, Gisela-Stein-Strasse 1, 81671 Munich, Germany  
[productinformation@wacker.com](mailto:productinformation@wacker.com), [www.wacker.com](http://www.wacker.com)

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.