

ELASTOSIL[®] M 4514

ELASTOSIL[®]

Room Temperature Curing Silicone Rubber (RTV-2)

Pourable, condensation-curing, two-component silicone rubber that vulcanizes at room temperature.

Main application: Making cost effective molds, especially for casting PE and PU resins.



Properties

- very good flowability and self-deaeration
- low Shore A hardness (approx. 25)
- excellent tear strength
- high elongation and flexibility
- outstanding chemical resistance to attack by polyester and polyurethane resins, mold life is significantly extended

Specific features

- Condensation-curing
- Flowable
- Resistance against polyester
- Resistance against PU
- Two-component

Technical data

Properties Uncured

Property	Condition	Value	Method
Color	-	white	-
Density	23 °C	1.26 g/cm ³	ISO 2811
Viscosity, dynamic after stirring	23 °C	35000 mPa·s	ISO 3219

These figures are only intended as a guide and should not be used in preparing specifications.

Catalyzed

with 5 wt % Catalyst T 51

Property	Condition	Value	Method
Viscosity, dynamic	23 °C	25000 mPa·s	ISO 3219

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

with 5 wt % Catalyst T 51, after 4 days at 23 °C / 50 % humidity

Property	Condition	Value	Method
Density in water	23 °C	1.25 g/cm ³	ISO 2781
Tear strength	-	> 25 N/mm	ASTM D 624 B
Hardness Shore A	-	25	DIN ISO 48-4
Tensile strength	-	4.5 N/mm ²	ISO 37
Elongation at break	-	450 %	ISO 37
Linear shrinkage	-	< 0.4 %	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Reproduction Molding

Application details

ELASTOSIL® M 4514 is a high-performance moldmaking compound, which is particularly suitable for the reproduction of models with extensive undercuts.

ELASTOSIL® M 4514 is especially suitable for the processing of polyester and polyurethane resins.

Processing

If molds for processing **epoxy or polyurethane resins** are to be made, ELASTOSIL® M 4514 is cured by adding 5 wt % Catalyst T 21.

For molds used to process other reproduction materials such as **polyester resins**, plaster, concrete, synthetic stone, wax or low-melting alloys, 5 wt % Catalyst T 51 should be used.

Catalyst	Pot life, [min]	Curing time (tack-free), [h]
5 % T 21	60-90	8-10
5 % T 51	60-90	8-10

The pot life is the period of time at 23 °C / 50 % rel. humidity during which the catalyzed mix to attain a viscosity of 100000 mPa s and still be just pourable.

For faster curing either catalyst may be blended with Catalyst T 47. E.g. at a ratio of 95 : 5 (T51 : T47) the pot life decreases to about 30 min, and the mold needs only about 4 h to cure.

Further instructions on blending any catalyst with Catalyst T 47 may be found in our data-sheet: "**WACKER® T-Series Catalysts**".

Please check also our brochures and info sheets.

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site www.wacker.com.

QR Code ELASTOSIL® M 4514



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Gisela-Stein-Strasse 1, 81671 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.