

ELASTOSIL® RT 426



Room Temperature Curing Silicone Rubber (RTV-2)

ELASTOSIL® RT 426 is a pourable, condensation-curing, two-component silicone rubber that vulcanizes at room temperature.

Main application: all-round potting compound

Properties

- Low viscosity
- High cured hardness
- Excellent heat resistance

Specific features

- Condensation-curing
- Flowable
- Heat resistant
- Two-component

Technical data

General Characteristics

Property	Condition	Value	Method
Density	20 °C	approx. 1.44 g/cm ³	DIN 53217
Viscosity, dynamic	23 °C	15000 - 25000 mPa·s	Brookfield

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Uncured

Property	Condition	Value	Method
Color	-	reddish brown	-

These figures are only intended as a guide and should not be used in preparing specifications.

Catalyzed

(catalyzed with 3 wt % Catalyst T 37, after 4 days at 23 °C / 50 % rel. humidity)

Property	Condition	Value	Method
Viscosity, dynamic	23 °C	10000 mPa·s	ISO 3219

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

Cure conditions: 190°C 10min

Property	Condition	Value	Method
Density in water	23 °C	1.44 g/cm ³	ISO 2781
Tear strength	-	> 4 N/mm	ASTM D 624 B
Hardness Shore A	-	60	ISO 868
Tensile strength	-	4.5 N/mm ²	ISO 37
Elongation at break	-	120 %	ISO 37
Linear shrinkage	-	0.8 %	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Electrics & Electronics
- Electronics
- Encapsulation

Application details

- all-round potting compound

Processing

Catalyst T 37 is admixed to ELASTOSIL® RT 426 for long, and Catalyst T 40 for short pot lives and curing times.

We recommend running preliminary tests to optimize conditions for the particular application. Comprehensive processing instructions are given in our leaflet "ROOM TEMPERATURE VULCANIZING (RTV) SILICONES" – Material and Processing Guideline

Catalyst	Pot life, approx. [min]	Curing time (tack-free), approx. [h]
3 % T 37	90	20-24
2 % T 40	40	3-4

The pot life is the period of time at 23 °C / 50 % rel. humidity during which the catalyzed mix to attain a viscosity of 100,000 mPa s and still be just pourable

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Being a condensation-curing silicone rubber, ELASTOSIL® RT 426 contains only constituents that over many years have proved to be neither toxic nor aggressive. Special handling precautions are therefore not required, i.e., only the general industrial hygiene regulations apply.

Catalysts T 37 and T 40 contain a tetraorganotin compound, are flammable and may cause irritation in contact with the eyes and skin. Adequate protective measures are required.

Please check also our brochures and info sheets.

QR Code ELASTOSIL® RT 426



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Gisela-Stein-Strasse 1, 81671 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.