

# SEMICOSIL<sup>®</sup> 986/1K



## 1-part heat-curing silicone rubber

SEMICOSIL<sup>®</sup> 986/1K is a non-slump, thermally curable, addition curing one-part silicone rubber.

### Properties

- ready-to-use, one-part system
- thixotropic
- translucent
- medium hardness
- high flexibility (low-stress-adhesive)
- primerless adhesion to many substrates
- rapid heat cure
- ultraviolet fluorescing

## Technical data

### Properties Uncured

Property	Condition	Value	Method
Viscosity, dynamic (D = 0.5 s <sup>-1</sup> )	25 °C	300000 mPa·s	ISO 3219
Viscosity, dynamic (D = 25 s <sup>-1</sup> )	25 °C	35000 mPa·s	ISO 3219
Color	-	translucent	-
Density	23 °C	1.07 g/cm <sup>3</sup>	DIN EN ISO 2811-1

These figures are only intended as a guide and should not be used in preparing specifications.

### Properties Cured

Cured for 30 min at 150 °C in a circulating air oven.

Property	Condition	Value	Method
Hardness Shore A	-	51	ISO 868
Tensile strength	-	5 N/mm <sup>2</sup>	DIN 53504 S2
Elongation at break	-	200 %	DIN 53504 S2
Tear strength	-	8 N/mm	ASTM D 624 B
Color	-	translucent	-
Density	23 °C	1.07 g/cm <sup>3</sup>	DIN EN ISO 1183-1 A
Modulus at 100 % elongation	-	3 N/mm <sup>2</sup>	ISO 37

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

## Applications

- Automotive Electronics
- Bonding & Sealing
- Electronic Control Unit (ECU)
- Electronics
- Power Control Unit (PCU)
- Power Electronics

## Application details

- general purpose adhesive for the electronics industry
- FIPG applications

## Processing

### Surface preparation

All surfaces must be clean and free of contaminants that will inhibit the cure of SEMICOSIL® 986/1K. Examples of inhibiting contaminants are sulfur containing materials, plasticizers, urethanes, amine containing materials and organometallic compounds – especially organotin compounds. If a substrate's ability to inhibit cure is unknown, a small scale test should be run to determine compatibility.

### Dispensing

Because of the thixotropy (shear thinning effect) SEMICOSIL® 986/1K can be dispensed easily with all dispensing equipments. Since silicones dissolve notable amounts of air, an in-line degassing is recommended.

### Curing

SEMICOSIL® 986/1K works best when cured at 115 °C or more depending on the size and heat sink properties of the components.

Temperature Curing time, thickness 10 mm

100°C 6 h

130°C 30 min

150 °C 10 min

### Adhesion

SEMICOSIL® 986/1K shows good primerless adhesion to many substrates. We recommend running preliminary tests to optimize conditions for the particular application.

## Packaging and storage

### Storage

The 'Best use before end' date of each batch is shown on the product label.

SEMICOSIL® 986/1K should be stored between +5 and +25°C in its tightly closed containers.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

## Safety notes

According to the latest findings, the addition-curing silicone rubber SEMICOSIL® 986/1K contains neither toxic or corrosive substances which would require special handling precautions.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

## QR Code SEMICOSIL® 986/1K



**For technical, quality or product safety questions, please contact:**

**Wacker Chemie AG**, Gisela-Stein-Strasse 1, 81671 Munich, Germany  
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.