

# SILPURAN® 6760/50 A/B



## Liquid Silicone Rubber (LSR)

Liquid silicone rubber of the SILPURAN® 6760 series is a paste-like, easily-pigmentable two-component compound with a very short curing time and good mechanical and electrical properties. Vulcanizates are noted for their self-adhesive properties to various substrates combined with a low coefficient of friction. SILPURAN® 6760/50 A/B is designed for medical applications in compliance with the WACKER SILICONES HEALTH CARE POLICY including implantation for < 30 days.

## Properties

SILPURAN® 6760/50 A/B meets selected test requirements of ISO 10993 and United States Pharmacopoeia (USP) Class VI. It is designed for medical applications in compliance with the WACKER SILICONES HEALTH CARE POLICY including implantation for < 30 days and is particularly suitable for the economical production of large series of injection molded articles.

SILPURAN® 6760/50 A/B is a primerless selfbonding grade that adheres to various thermoplasts (e.g. PA, PBT) and metals. The bonding is improved by an ageing process (e.g. one hour at 100 °C) or by a longer storage at room temperature. Because of the individual surface properties each substrate must be tested before starting mass production. If necessary, one has to check the development of adhesive properties over time and/or in an environment relevant to the application.

Compared to the SILPURAN® 6000 series the coefficient of friction of an article of SILPURAN® 6760 is reduced by 50 - 70 %.

At service temperatures above approx. 180 °C the addition of heat stabilizers is recommended. Further information about an improvement of the heat stability by use of specific ELASTOSIL® Color Pastes FL can be obtained from the Technical Information Sheet "ELASTOSIL® Color Pastes FL" or the latest edition of our brochures.

## Specific features

- Food-contact
- Less self-healing
- Low coefficient of friction
- Reduced volatile content
- Self-adhesive

## Technical data

### Properties Uncured

Property	Condition	Value	Method
Viscosity, dynamic (1 s <sup>-1</sup> )	-	870000 mPa·s	DIN EN ISO 3219
Viscosity, dynamic (10 s <sup>-1</sup> )	-	320000 mPa·s	DIN EN ISO 3219

These figures are only intended as a guide and should not be used in preparing specifications.

### Properties Cured

Cure conditions: 5 min / 165 °C in press, non post-cured

Property	Condition	Value	Method
Appearance	-	transparent	-
Hardness Shore A	-	50	DIN ISO 48-4
Hardness Shore A <sup>(1)</sup>	-	63	DIN ISO 48-4
Density	-	1.10 g/cm <sup>3</sup>	DIN EN ISO 1183-1 A
Tensile strength	-	8.4 N/mm <sup>2</sup>	ISO 37 type 1
Elongation at break	-	600 %	ISO 37 type 1
Tear strength	-	27 N/mm	ASTM D 624 B

<sup>1</sup>Post-cured: 4 h / 200 °C

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

## Applications

- Medical Devices

### Application details

The following studies were performed on vulcanizates of SILPURAN® 6760/50 A/B according to ISO 10993:

- Cytotoxicity (ISO 10993-5)
- Sensitation LLNA (ISO 10993-10)
- Pyrogenicity (ISO 10993-11)

The following studies were performed on vulcanizates of SILPURAN® 6760/50 A/B according to USP class VI:

- Acute systemic toxicity
- Intracutaneous toxicity

- Implantation test

No adverse effects have been detected at any of the studies performed.

Properly cured and post-cured vulcanizates of SILPURAN® 6760/50 A/B can be used for food contact applications and are suitable for use under the Recommendation "XV. Silicones" of the BfR and FDA 21 CFR §177.2600 "Rubber Articles Intended for Repeated Use" considering any given limitations on extractable and volatile substances.

## Processing

The A and B components are delivered ready to use in 20 kg pail kits. With adequate metering equipment, they can be pumped directly from the original containers into the injection molding machine and mixed by a static mixer. The mixing ratio is 1 : 1. At room temperature, mixtures of A and B components have a pot life of at least three days.

For detailed information please refer to the latest edition of our brochure "SOLID AND LIQUID SILICONE RUBBER - MATERIAL AND PROCESSING GUIDELINES".

## Packaging and storage

### Packaging

This product is available in 20 kg pail kits.

SILPURAN® is neither produced nor packed under sterile conditions, so the final product has to be sterilized prior to use, if necessary.

### Storage

Once opened, containers should always be resealed after use to prevent the platinum catalyst from being poisoned by amines, sulphur or phosphorus compounds. For detailed information about storage conditions please refer to the latest edition of our brochure "SOLID AND LIQUID SILICONE RUBBER - MATERIAL AND PROCESSING GUIDELINES".

The 'Best use before end' date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

## Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

## QR Code SILPURAN® 6760/50 A/B



### For technical, quality or product safety questions, please contact:

**Wacker Chemie AG**, Gisela-Stein-Strasse 1, 81671 Munich, Germany  
[productinformation@wacker.com](mailto:productinformation@wacker.com), [www.wacker.com](http://www.wacker.com)

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.